



TECHNICAL DATASHEET

DIJMID PA 6 GF 10

Polyamide 6 compound 10% glass fiber reinforced | Colour: Black for injection moulding

Property	Method	Measurement condition	Unit	Values
Melt flow rate	ISO 1133	275 °C / 5 kg	cm ³ /10 min	80
Density	ISO 1183	-	kg/m ³	1310
				Dry as moulded
Tensile modulus	ISO 527-1	1 mm/min	MPa	4000
Tensile stress at break	ISO 527-1	5 mm/min	MPa	80
Tensile strain at break	ISO 527-1	5 mm/min	%	3
Charpy Impact Strength at 23 °C	ISO 179/1A	unnotched	KJ/m ²	25
Charpy Impact Strength at 23 °C	ISO 179/1A	notched	KJ/m ²	4
Melting Point	ISO 11357-1	DSC	°C	220

Application data

Description	Black opaque 10% glassfilled Polyamid with good flow.
Application	Injection Moulding
Drying conditions	80 °C , 4-6 hours moisture content < 0,15%
Moulding temperature - Nozzle	270 - 290 °C
Moulding temperature - Barrel	270 - 280 °C
Mold Temperature	85 - 95 °C
Compression ratio	2:1 - 2,5:1
Injection Pressure	90% of ram travel
Injection Speed	Fast ram speed
Hold pressure	Low
Screw speed	0,1 - 0,2 m/s
Cushion	4 - 6 mm
Back pressure	0 - 3,0 MPa

This information contained in this document is based on testing carried out by our laboratory. To the best of our knowledge and at the time of publication, this information is true and accurate. It shall however, in no event be held to constitute or imply warranty, undertaking express or implied commitment from the part of supplier. No liability whatsoever can be accepted by supplier with regard to the handling, processing or use of the product concerned which must in all cases be used in accordance with all applicable laws and regulations. Material is conform RoHS and Reach regulations and without heavy metals rev.date 28 03 2017.

Document version 1 | Release date: December 2020.