



## TECHNICAL DATASHEET

# DIJPROP 05 GF 30

Polypropylene compound Glass 30 | Colour: Black

Property	Method	Measurement condition	Unit	Values
Melt flow rate	ISO 1133	230 °C; 2,1 kg	g /10 min	5
Ash content	ISO 3451	800 °C, 30 min	%	40 ± 2
Izod Impact Strength at 23 °C	ISO 180	notched	kJ/m <sup>2</sup>	8
Flexural Modulus	ISO 178	2 mm/min	MPa	8200
Flexural Yield Strength	ISO 178	2 mm/min	MPa	138
Tensile strength	ISO 527-1	5 mm/min	MPa	90
Elongation at break	ISO 527-1	5 mm/min	%	4
Heat Deflection Temperature	ISO 75A	A	°C	151
Vicat Temperature	ISO 306	50N; 50°C/h	°C	161
Density	ISO 1183-1	method A	g/cm <sup>3</sup>	1,21
Burning Behavior	UL - 94	1,6	mm	HB
Moldschrinkage	Inhouse method		%	0,3-0,7

### Application data

Description	Black PP compound with 30% glasfiber
Application	Injection Moulding
Drying conditions	80 °C , 4-6 hours moisture content < 0,02%
Moulding temperature - Nozzle	240 - 260 °C
Moulding temperature - Barrel	210 - 255 °C
Mold Temperature	40 - 80 °C
Compression ratio	2:1 - 2,5:1
Injection Pressure	Low
Injection Speed	Fast ram speed
Hold pressure	Low
Screw speed	0,1 - 0,2 m/s
Cushion	4 - 6 mm
Back pressure	0 - 1,0 MPa

This information contained in this document is based on testing carried out by our laboratory. To the best of our knowledge and at the time of publication, this information is true and accurate. It shall however, in no event be held to constitute or imply warranty, undertaking express or implied commitment from the part of supplier. No liability whatsoever can be accepted by supplier with regard to the handling, processing or use of the product concerned which must in all cases be used in accordance with all applicable laws and regulations. Material is conform RoHS and Reach regulations and without heavy metals rev.date 28 03 2017.

Document version 1 | Release date: December 2020.