

Polycarbonate injection molding type | Colour: Black/Compound glassfilled 30% UV stablized

Property	Method	Measurement condition	Unit	Values
Melt Flow Rate	ISO 1133	300 °C; 1,2 kg	g /10 min	12
Izod Impact Strength at 23 °C	ISO 180	notched	kJ/m ²	6
Tensile Modulus	ISO 527-1	1 mm/min	MPa	6100
Tensile strength	ISO 527-1	5 mm/min	MPa	70
Flexural-modulus	ISO 527-1	2 mm/min	MPa	6000
Heat Deflection Temperature	ISO 75A	A	°C	139
Vicat Temperature	ISO 306	50N; 50°C/h	°C	146
Shore hardness	ISO 868	D		78
Density	ISO 1183-1	method A	g/cm ³	1,44
Burning Behavior	UL - 94	1,6	mm	V-1
Burning rate (US-FMVSS)	ISO 3795	>=1.0 mm	mm/min	passed
Moldschrinkage	Inhouse method		%	0,3-0,7

Application data

Description	Black opaque 30% glassfilled PolyCarbonate with good flow. with UV stablization
Application	Injection Moulding
Drying conditions	120 °C , 4-6 hours moisture content < 0,02%
Moulding temperature - Nozzle	280 - 320 °C
Moulding temperature - Barrel	270 - 320 °C
Mould Temperature	80 - 120 °C
Compression ratio	2:1 - 2,5:1
Injection Pressure	Low
Injection Speed	Fast ram speed
Hold Pressure	Low
Screw speed	0,1 - 0,2 m/s
Cushion	4 - 6 mm
Back Pressure	0 - 1,0 MPa

This information contained in this document is based on testing carried out by our laboratory. To the best of our knowledge and at the time of publication, this information is true and accurate. It shall however, in no event be held to constitute or imply warranty, undertaking express or implied commitment from the part of supplier. No liability whatsoever can be accepted by supplier with regard to the handling, processing or use of the product concerned which must in all cases be used in accordance with all applicable laws and regulations. Material is conform RoHS and Reach regulations and without heavy metals rev.date 28 03 2017

